

Europälaches Patentamt

European Patent Office

Office ouropéen des brevets



(11) EP 1 086 981 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

- (43) Date of publication: 28.03.2001 Builetin 2001/13
- (21) Application number: 99913656.7
- (22) Date of filing, 13,04,1999

- (51) Int. CI.7: CO8J 7/04, B32B 9/00
- (86) International application number: PCT/JP99/01989
- (87) International publication number: WO 99/52973 (21.18.1999 Gazette 1999/42)
- (84) Designated Contracting States: DE FR GB IT NL
- (30) Priority: 15.04.1998 JP 12183598 12.04.1999 JP 10452399
- (71) Applicant: Kuraha Chemical Industry Co., Ltd. Tokyo 103-0012 (JP)
- (72) Inventors:
 - OHBA, Hiroyuki, Kureha Chemical Industry Co., Ltd Nilheri-gun, ibaraki 311-3436 (JP)
 - TANAKA, Hideski, Kureha Chemical Industry Co., Ltd Nilhari-gun, ibaraki 311-3438 (JP)

- SATO, Tomoski, Kurcha Chomical Industry Co., Ltd NBharl-gun, Ibaraki 311-3436 (JP)
- HASEGAWA, Tomohisa,
 Kuroha Chemical Ind. Co., Ltd
 NBhari-gun, Ibaraki 311-3436 (JP)
- SAIKA, Toru,
 Kurche Chemical Industry Co., Ltd.
 Nilharl-gun, ibaraki 311-3436 (JP)
- (74) Representative:
 Benson, John Everett
 J. A. Kemp & Co.,
 14 South Square,
 Gray's Inn
 London WC1R 5LX (GB)

(54) GAS-BARRIER FILMS

(57) The present invention provides a gas-barrier film which is produced through applying a layer consulting a metallic compound to a surface of a processed-polymer layer produced from a mixture of a polyalcohol and at least one poly(meth)acrylic polymer selected from the group consisting of poly(meth)acrylic acids and partially neutralized poly(meth)acrylic acids. The invention also provides a laminated gas-barrier film containing the aforementioned gas-barrier film either surface of which is laminated on with a plastic film. The gas-barrier film exhibits excellent gas-barrier properties and can be produced through a simple, convenient process.

EP 1 086 981 A1

Table 6

			_					
8		Oxygen Permeability		Water resistance Ra (µ		(µm)	μm) Existence ratio of metal compound	
		Pre*8	Post*8		AFM	TEM		
10	Ex. 51	0.3	0.1	0	0.003	0.02	1.58	
	Ex. 52	0.8	4.0	0	0.003	0.02	2.60	
	Ex. 53	0.2	0.2	0	0.003	0.02	2.50	
	Ex. 54	0.4	0.9	٥	0.004	0.02	1.56	
15	Ex. 55	0.5	1.0	0	0.004	0.02	1.56	
	Ex. 68	0.3	1.0	0	0.003	0.02	1.56	
	Ex. 57	0.3	1.0	0	0.003	0.02	1.56	
	Ex. 58	<0.1	<0.1	0	0.003	0.02	1,58	
20	Comp. Ex. 11	13	50	0	-		0	
	Comp. Ex. 12	1.0	14	0	١.		o	
	Comp. Ex. 13	0.5	20	0	-		0	
25	Сотр. Ех. 14	0.9	40	0	-		٥	
	Comp. Ex. 15	3.5	14	0			0	
	Comp. Ex. 16	40	100	0			o	
	Comp. Ex. 17	1.0	14	0	. ;		o	
30	Comp. Ex. 18	0.4	15	0	-		o	
	Comp. Ex. 19	122	140	0	•	-	0	
28	Comp. Ex. 20	77	130	0		•	o	
	Comp. Ex. 21	30	110	0	•		0	
	Cemp. Ex. 22	6.2	47	0	0.003	0.02	0	
	Comp. Ex. 23	5.9	47	0	0.015	0.06	0	
	Comp. Ex. 24	1.0	14	0	0.015	0.02	o	
40	Comp. Ex. 25	1.0	14	o	0.001	0 0004	o	

Pre'8); Measurement before retort treatment Post'8); Measurement after retort treatment

45 Industrial Applicability

[0123] When a metallic compound is applied to a polymer layer, the produced film axhibits excellent gas-berrier properties. Application of a metallic compound is carried out through a simple, convenient, and inexpensive process as compared with the deposition process. When a polymer layer is heat-treated, water resistance is imparted to the layer, and thus a gas-barrier film exhibiting water resistance and excellent oxygen gas-barrier properties can be produced, and the gas barrier properties of the film are not impaired through washing with water.

Claime

4. A gas-barrier film which is produced through applying a layer containing a metallic compound onto a surface of a polymer layer produced from a mixture of a polyalcohol and at least one poly(meth)acrylic acid polymer selected from the group consisting of poly(meth)acrylic acids and partially neutralized poly(meth)acrylic acids.

EP 1 086 981 A1

- A gas-barrier film according to claim 1, wherein the surface of the polymer layer to which the metallic-compoundcontaining layer is not applied is fixed onto a surface of a substrate.
- 3. A gas-barrier film according to claim 1, wherein at least the polymer layer is subjected to heat treatment.
- 4. A gas-berrier film according to claim 1, wherein the metallic compound is at least one species selected from the group consisting of magnesium oxide, calcium oxide, zinc oxide, magnesium hydroxide, calcium hydroxide, and zinc hydroxide.
- 10 S. A gas-barrier film according to claim 1, wherein the metallic-compound-containing layer is produced from a mixture of the metallic compound and a resin.
 - 6. A gas-barner film according to claim 5, wherein the film is used for starilization treatment.

20

45

50

25

7. A laminated gas-barrier film comprising a gas-barrier film according to any one of claims 1 through 6, wherein a plastic film is laminated on either surface of the gas-barrier film.